



型号(①代码·②D) — ③V — ④T
EAHCW25 — 6 — 1

■请按步骤①~④选择型号和参数后进行订购。



型号区分: ⑦天发货
代码

■环型

EAHCW

2-C0.1~0.5
N S
2-C0.1~0.5
磁化方向: 厚度方向

③V_{+0.3}/_{+0.1}
②D_{-0.2}
④T_{±0.1}

① N极划线或点

代码	材质	表面处理	耐热温度
EAHCW	钕磁铁	镀镍	80℃

型号		③V 选择	④T	吸引力 N {kgf}	表面磁通密度 高斯 [G]
①代码	②D				
EAHCW	6	2	2	6.2 {0.6}	2600~2800
			3	8.0 {0.8}	3200~3400
			1	4.9 {0.5}	1600~1800
	8	3 4	2	7.8 {0.8}	2600~2800
			3	9.8 {1.0}	3200~3400
			5	14.3 {1.5}	3200~3800
	10	3 4 5 6	1	6.9 {0.7}	1700~1900
			2	10.8 {1.1}	2600~2800
	12	4 5 6 8	3	11.8 {1.2}	3200~3400
			5	18.8 {1.9}	3600~3800
	14	6 8	1	7.8 {0.8}	1500~1700
			2	13.7 {1.4}	2500~2700
18	6 8 12	3	15.7 {1.6}	2900~3100	
		5	23.3 {2.4}	3600~3800	
20	6 8 10 12	1	8.8 {0.9}	1600~1800	
		2	19.6 {2.0}	2600~2800	
25	6 8 10 12	3	23.5 {2.4}	2900~3100	
		5	36.0 {3.7}	3600~3800	
30	6 12 5	3	48.6 {5.0}	2900~3100	
		5	10.8 {1.1}	1300~1500	
30	6 12 5	2	21.6 {2.2}	2200~2400	
		3	33.3 {3.4}	2600~2800	
30	6 12 5	1	12.7 {1.3}	1300~1500	
		2	34.3 {3.5}	2100~2300	
30	6 12 5	3	58.8 {6.0}	2600~2800	
		5	73.8 {7.5}	3400~3600	
30	6 12 5	1	98.5 {10.0}	3000~3200	



■请按步骤①~④选择型号和参数后进行订购。

●MGLN 型号(①代码·②A) — ③B — ④T
EAMLN10 — 5 — 1

●MGLF 型号(①代码·②T) — ③A — ④B
MGLF10 — 30 — 60



型号区分: ⑦天发货
代码

■方型

磁化方向: 厚度方向

③B_{0-0.1}
②A_{0-0.1}
④T_{0-0.1}

① N极划线或点

代码	材质	表面处理	耐热温度
EAMLN	钕磁铁	镀镍	80℃
EAMLF	铁氧体磁铁	—	300℃

钕磁铁 EAMLN

铁氧体磁铁 EAMLF

③B_{0-0.1}
②A_{0-0.1}
④T_{±0.1}

① N极划线或点

型号		③B	④T	吸引力 N {kgf}	表面磁通密度 高斯 [G]
①代码	②A				
EAMLN (钕磁铁)	3	3	3	2.8 {0.29}	4100~4300
			4	5.6 {0.57}	4300~4500
			5	8.9 {0.91}	4400~4600
	5	5	6	13.7 {1.4}	4500~4700
			8	23.2 {2.37}	4400~4600
			1	2.7 {0.28}	1700~1900
	10	5	2	8.5 {0.87}	3000~3200
			5	16.8 {1.71}	4200~4400
			1	6.5 {0.66}	1800~2000
	10	10	2	11.8 {1.2}	2500~2700
			8	39.3 {4.01}	4500~4700
			3	13.9 {1.42}	3100~3300
15	5	5	23.7 {2.42}	4100~4300	
		10	31.4 {3.2}	4700~4900	
		3	23.9 {2.44}	2900~3100	
15	10	5	34.3 {3.5}	3300~3700	
		10	61.4 {6.27}	4600~4800	
		5	40.8 {4.16}	4600~4800	
20	10	5	47.7 {4.87}	3500~3700	
		10	77.8 {7.94}	4700~4900	
		15	69.7 {7.11}	3300~3700	
30	20	5	84.8 {8.65}	3100~3300	
		30	110.8 {11.31}	3300~3700	

型号		③A	④B	吸引力 N {kgf}	表面磁通密度 高斯 [G]	A公差	B公差
①代码	②T						
EAMLF (铁氧体磁铁)	5	10	5	1.6 {0.16}	900~1100	±0.1	±0.1
			10	4.9 {0.50}			
			20	9.8 {1.00}			
			30	12.7 {1.30}			
	10	30	30	21.6 {2.20}	1100~1400	±0.15	±0.15
			30	29.4 {3.00}			
			20	17.7 {1.80}			
			40	31.4 {3.20}			